



ZISTA Group

www.zista.co

Bitumen 60/70

Specific Gravity @ 25/25°C	1.01-1.06	ASTM D-70
Penetration @ 25°C	60-70	ASTM D-5
Softening Point°C	49-56	ASTM D-36
Ductility @ 25°C	100min	ASTM D-113
Loss On Heating %wt	0.2max	ASTM D-6
Drop In penetration After Heating %	20max	ASTM D-6&D-5
Flash Point°C	250min	ASTM D-92
Solubility In TCE %wt	99.5min	ASTM D-4