



ZISTA Group

www.zista.co

Bitumen 80/100

Specific Gravity @ 25/25°C	1.01-1.05	ASTM D-70
Penetration @ 25°C	80-100	ASTM D-5
Softening Point°C	43 min	ASTM D-36
Ductility @ 25°C	100min	ASTM D-113
Loss On Heating %wt	0.5max	ASTM D-6
Drop In penetration After Heating %	20max	ASTM D-6&D-5
Flash Point°C	225min	ASTM D-92
Solubility In TCE %wt	99 min	ASTM D-4